










# 郑州市海旭磨料有限公司

## zhengzhou haixu abrasives Co.,Ltd.



地址：河南省郑州市桐柏路与陇海路交叉口凯旋门大厦A座0801室  
 电话：0371-60305638 60305639 传真：0371-60305637

### White Fused Alumina(WFA)

WA Size	Picture	Chemical Analysis(%)		
		Al <sub>2</sub> O <sub>3</sub>	Fe <sub>2</sub> O <sub>3</sub>	Na <sub>2</sub> O
<b>0-11-3 3-5 5-8mm</b> ... ..		99.60min	0.04max	0.28max
<b>F8-F60</b>		99.55min	0.04max	0.23max
<b>F70-F220</b>		99.55min	0.04max	0.23max
<b>F240-F320</b>		99.53min	0.04max	0.25max
<b>F360-F500</b>		99.43min	0.05max	0.27max
<b>F600-F1000</b>		99.27min	0.06max	0.30max
<b>F1200</b>		99.18min	0.06max	0.32max

<b>Bulk density</b>	1.75-1.95g/cm <sup>3</sup>
<b>Real density</b>	3.95-3.97g/cm <sup>3</sup>
<b>Mohs</b>	9.0

### Brown Fused Alumina (BFA)

Size \ A	Picture	Chemical Analysis(%)		
		Al <sub>2</sub> O <sub>3</sub>	Fe <sub>2</sub> O <sub>3</sub>	SiO <sub>2</sub>
<b>0-1 1-3 3-5 5-8mm...</b>		95.00min	0.20max	1.50max
<b>F8-F40</b>		95.00min	0.30max	1.78max
<b>F46-F220</b>		95.00min	0.30max	1.78max
<b>F230-F1200</b>		99.25min	0.60max	2.00max
<b>Bulk density</b>	1.53-1.99g/cm <sup>3</sup>			
<b>Real density</b>	3.95-4.0g/cm <sup>3</sup>			
<b>Mohs</b>	9.0			

**Packing:**25kgs PVC bags+1MT big bag

TEL: 86-371-60305639

MP: 86-15838373120

MSN:[haixu\\_sunshine@hotmail.com](mailto:haixu_sunshine@hotmail.com)

ADD: A#801 Kaixuanmen, Tongbai South road, Zhengzhou City, Henan Province, China

FAX: 86-371-60305637

Email:[sales@zzhaixu.cn](mailto:sales@zzhaixu.cn)

Skype: sunshinema90